## **TECHNICAL DATA SHEET**

Masterbatch series



282 Moo 2 Phraek Sa Mai, Amphoe Mueang Samut Prakan, Samut Prakan 10280, Thailand

Tax ID: 0115559016356 Website: Unique-polymer.com

## XP-2002 Polymer processing aid

Intended to aid converters in achieving better processing conditions and products. Contains fluorine-based additives which is ideal for coating the inside of die wall and reducing friction between resin and die. Expect longer continuous running with reduced die build up and more uniform unrestricted polymer flow with lower extruder and die head pressure. Products will also have better optical properties with the elimination of melt fracture. Designed to be used for blown film, injection molding, blow molding, pipe and rod extrusion, and profile extrusion.

**Product description:** XP-2002 contains 2% fluoropolymer content with addition of antioxidants to improve

thermal stability. PPA masterbatch appearance is translucent with no tint.

## Technical data:

Properties	Value
Polymer carrier	LLDPE
Fluoropolymer content (%)	2
Density (g/cm3)	0.98
MFR 190°C/2.16 kg (g/10min)	6.0
Moisture content (%)	<0.1
Bulk density (g/cm³)	0.60

**Standard packaging:** XP-2002 masterbacthes will be delivered in 25kg PE bags. Other packaging and labelling

are also available upon request. Product will be arranged on top of wooden pallets for

easy handling.

**Storage instruction:** Recommended to be used within 18 months of the production date. Product should be

stored under dry, cool conditions protected from direct sun light. Other storage conditions

may impair the quality of the masterbatch.

**Declarations:** Based on declarations received from our suppliers, materials in this ingredient are in

compliance with international standard regulations such as U.S. FDA 21 CFR 177.1520

and RoHS according to 2002/95/EC.

Revision (DD.MM.YYYY): 15.02.2021